

Target : To test a sample of 1 dm² minimum, according to NF EN ISO 9227 after the protection of the 2 ending parts of the sample

Diameter (mm)	Length sample to cut (mm)	Distance from the ending parts of the sample (mm)
16	350	150
18 to 25,4	350	120
28 to 30	300	120
31,75 to 40	250	120
42 to 50,80	200	120
52 to 55	170	120
56 to 65	150	120
69,85 to 80	120	120
82,55 to 100	100	120
110 to 125	80	120
130 to 160	70	120