PARAMETERS CHECKING - SALT SPRAY TEST

Salt Spray test according to : NF EN ISO 9227
Type of test : Neutral
SALT SPRAY CABINET

Date	Start of the test	Deionised water		Stock solution			Temperature °C Cabinet	Temperature °C Humidifier	Pression in Bars	% NaCl	Collection of water				Preparation of the test tube with funnel		Inclination angle of the samples	Action	Name
				NaCl Pure	Density (25°C)	pH					Volume in 24h		pH measured						
											Left	Right	Left	Right	Cleaning	Protection			
		25°C +/- 2	**≤ 20 µS/cm**	**4,5 à 5,5%**	**1,0255-1,04**	**6,0 - 7,0**	**35 +/- 2**	**> 40**	**0,7 - 1,7**	**4,5 à 5,5%**	**24- 48**	**24 - 48**	**6,5 - 7,2**	**6,5 - 7,2**	**Acetone**	**varnish**	**20° +/-5**		
1/6	15h	25°C	18	5,5	1,059	6,30	35,0	40	1,1	4,6	27	28	6,75	6,74	Acetone	varnish	20° +/-5	Add solution + Adjustement pH	A,A
2/6																			
3/6																			
4/6	10h	25°C	19	5,5	1,059	6,30	34,8	40	1,1	4,7	28	29	6,7	6,78	Acetone	varnish	20° +/-5	Add solution + Adjustement pH	A,A
5/6	11h	25°C	17	5,5	1,059	6,30	34,9	40	1,1	4,8	30	31	6,78	6,74	Acetone	varnish	20° +/-5	Control of the stock solution	A,A
6/6	14H	25°C	16	5,5	1,059	6,31	35,0	40	1,1	4,6	29	28	6,75	6,75	Acetone	varnish	20° +/-5	Control of the stock solution	A,A
7/6	14H30	25°C	16	5,5	1,059	6,30	34,8	40	1,1	4,8	30	27	6,74	6,72	Acetone	varnish	20° +/-5	Control of the stock solution	A,A
8/6	15H	25°C	16	5,5	1,059	6,34	35,1	40	1,1	4,7	27	28	6,76	6,72	Acetone	varnish	20° +/-5	Add solution + Adjustement pH	A,A
9/6																			
10/6																			
11/6	10H30	25°C	17	5,5	1,059	6,3	34,7	40	1,1	4,8	27	26	6,67	6,69	Acetone	varnish	20° +/-5	Add solution + Adjustement pH	A,A
12/6	11H	25°C	17	5,5	1,059	6,31	34,8	40	1,1	4,6	28	28	6,7	6,68	Acetone	varnish	20° +/-5	Control of the stock solution	A,A
13/6	14H	25°C	18	5,5	1,059	6,31	35,0	40	1,1	4,8	29	31	6,71	6,67	Acetone	varnish	20° +/-5	Control of the stock solution	A,A
14/6	14H30	25°C	17	5,5	1,059	6,31	35,0	40	1,1	4,7	31	37	6,71	6,72	Acetone	varnish	20° +/-5	Control of the stock solution	A,A
15/6	15H	25°C	19	5,5	1,059	6,3	34,9	40	1,1	4,9	27	25	6,7	6,71	Acetone	varnish	20° +/-5	Add solution + Adjustement pH	A,A
16/6																			
17/6																			
18/6	10H30	25°C	17	5,5	1,059	6,31	34,8	40	1,1	4,7	29	30	6,67	6,69	Acetone	varnish	20° +/-5	Add solution + Adjustement pH	A,A
19/6	11H	25°C	18	5,5	1,059	6,30	34,8	40	1,1	4,8	27	27	6,79	6,72	Acetone	varnish	20° +/-5	Control of the stock solution	A,A
20/6	11H30	25°C	17	5,5	1,059	6,31	34,9	40	1,1	4,56	26	24	6,76	6,74	Acetone	varnish	20° +/-5	Control of the stock solution	A,A
21/6	14H	25°C	18	5,5	1,059	6,32	35,0	40	1,1	4,57	28	25	6,79	6,72	Acetone	varnish	20° +/-5	Control of the stock solution	A,A
22/6	14H30	25°C	17	5,5	1,059	6,31	35,1	40	1,1	4,51	29	23	6,81	6,73	Acetone	varnish	20° +/-5	Add solution + Adjustement pH	A,A
23/6																			
24/6																			
25/6	10H	25°C	18	5,5	1,059	6,34	34,7	40	1,1	5,0	27	26	6,81	6,74	Acetone	varnish	20° +/-5	Add solution + Adjustement pH	A,A
26/6	10H30	25°C	18	5,5	1,059	6,34	34,8	40	1,1	4,9	29	29	6,80	6,76	Acetone	varnish	20° +/-5	Control of the stock solution	A,A
27/6	11H	25°C	17	5,5	1,059	6,35	34,8	40	1,1	5,0	31	31	6,81	6,75	Acetone	varnish	20° +/-5	Control of the stock solution	A,A
28/6	11H30	25°C	18	5,5	1,059	6,34	34,9	40	1,1	5,0	31	34	6,78	6,78	Acetone	varnish	20° +/-5	Control of the stock solution	A,A
29/6	14H	25°C	17	5,5	1,059	6,35	35,1	40	1,1	5,0	37	28	6,77	6,79	Acetone	varnish	20° +/-5	Add solution + Adjustement pH	A,A
30/6																			