

## Aggressivity test according to NF A05-109

### Results :

The aggressivity of the cabinet is compliant if 5% minimum of the surface of the aggressivity plaque is oxidated between 73 and 120 hours

Hours	Rouille rouge	Conformité
<b><math>\leq 72</math></b>	<b>5% de la surface oxydée minimum</b>	<b>Not OK = too much aggressive</b>
<b>73 to 120</b>		<b>OK</b>
<b><math>&gt; 121</math></b>		<b>Not OK = not enough aggressive</b>